

Coal Fillers Inc.

AUSTIN BLACK 325 PRODUCT SPECIFICATION

<u>Physical Properties</u>	<u>Test Method</u>	<u>Values</u>
Specific gravity:	ASTM D 1817-01	1.31+/-0.03
Carbon, C:	-----	77.00% typical
Volatiles:	ASTM D 3175	20.00% max.
Moistures (Heat Loss)	ASTM D3302	1.00% max.
Ash:	ASTM D3174	7.5% max.
Sulphur:	ASTM D3177	0.80% +/-0.10%
pH:	ASTM D 1512	7.00
Screen Analysis	CFI Test Procedure	Maximum .1%retained on 325 mesh Maximum .0005% retained on 100 mesh
Particle size:	Microtrac SRA 150	6.00 microns maximum average